

# LEXAN™ 6070 FILM

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ 6070 Film is a co-extruded film with improved scratch resistance and a high gloss surface finish. The film has excellent clarity, high heat resistance and excellent formability. LEXAN 6070 Film also provide good dimensional stability and improved pencil hardness. Masking are available on both sides.

### TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
<b>MECHANICAL</b>						
Tensile Strength @ Yield	ASTM D882	psi	8920	ISO 527	MPa	61.5
Ultimate	ASTM D882	psi	7107	ISO 527	MPa	49
Tensile Modulus	ASTM D882	psi	313424	ISO 527	MPa	2161
Tensile Elongation at Break (TD/MD)	ASTM D882	%	24	ISO 527	%	24
<b>THERMAL</b>						
Coefficient of Thermal Expansion						
CTE -20~60°C, crossflow	ASTM E831	( $\times 10^{-5}$ )/°F	0.29	ISO 11359-2	( $\times 10^{-5}$ )/°C	7.4
CTE -20~60°C, inflow	ASTM D831	( $\times 10^{-5}$ )/°F	0.24	ISO 11359-2	( $\times 10^{-5}$ )/°C	7.4
<b>PHYSICAL</b>						
Density	ASTM D792	slug/ft <sup>3</sup>	2.33	ISO 1183	g/m <sup>3</sup>	1.19
Water Absorption, 24 hrs.	ASTM D570	% change	0.41	ISO 62	% change	0.11
Pencil hardness (500g)	ASTM D3363	-	1H	-	-	1H
Taber Abrasion (100 Cycles)	ASTM D1044	Delta Haze%	22.6	-	Delta Haze%	22.6
Surface Tension (PMMA surface/ PC surface)	Dyne Pens	Dyne	38/40	-	Dyne	38/40
<b>OPTICAL</b>						
First surface			1.49			
Second surface			1.58			
Light Transmission	ASTM D1003	%	92.1	ISO 489		92.1
Yellowness Index	ASTM E313	%	0.4/0.57			0.4/0.57
Haze	ASTM D1003	%	0.1			0.1
Gloss over Flat Black	ASTM D523-60	-		ISO 2813		
@ 20°			83.2			83.2
@ 60°			88.3			88.3
@ 85° (PMMA surface)			97.7			97.7

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department. Reported values are based on 0.250 mm (0.010") thickness film and are tested at machine direction unless otherwise noted.

™ Trademark of SABIC.

## MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.007" (0.178mm)	-/+ 10%
0.010"-0.015" (0.178mm-0.381 mm)	-/+ 5%

### SABIC HQ

PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
F +966 (0) 1 225 9000  
E [info@sabic.com](mailto:info@sabic.com)

### AMERICAS

SABIC  
Specialty Film & Sheet  
One Plastics Avenue  
Pittsfield, MA 01201  
USA  
T 1 800 323 3783 (toll-free)  
T 1 413 448 6655  
F (888) 443 2033  
E [Spinside.sales@sabic-ip.com](mailto:Spinside.sales@sabic-ip.com)

### EUROPE

SABIC  
Specialty Film & Sheet  
Plasticslaan 1  
4612 PX Bergen op Zoom  
The Netherlands  
T +31 164 293684  
F +31 164 292272  
E [sfs.info@sabic-ip.com](mailto:sfs.info@sabic-ip.com)

### PACIFIC

SABIC  
Specialty Film & Sheet  
1266 Nanjing Road (A)  
16th Floor, Plaza 66  
200040 Shanghai  
China  
T +86 21 62881088 ext. 6733  
F +86 21 6288 0818  
E [sfs.info@sabic-ip.com](mailto:sfs.info@sabic-ip.com)

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.  
© 2013 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

<sup>1</sup> Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

[www.sabic.com/sfs](http://www.sabic.com/sfs)

