

LEXAN™ OQ92W FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ OQ92W optical film is a high-performance coated film which may offer very good chemical/abrasion/UV resistance, together with improved surface quality and tighten gauge variation over standard LEXAN HP92W film. This highly durable, easily printed film may help create new opportunities in outdoor graphic applications.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS (USCS)	VALUE
PHYSICAL			
Specific Gravity	ASTM D792 / ISO 1183	g/cm ³	1.2
Surface Energy (Coated surface/ Uncoated surface)	ASTM D5946-01	dynes/cm	(41/32)
Pencil Hardness (Coated surface/ Uncoated surface)	ASTM D3363-05	--	(HB/3B)
Taber Abrasion	ASTM D1044-05	delta Haze%	5.15
OPTICAL			
Haze (Average)	ASTM D1003 / ISO14782	%	0.7
Light Transmission	ASTM D1003 / ISO13468	%	91
Yellowness Index	ASTM D1925	--	0.8
Specular Gloss	ASTM D523-89	--	160
UV % transmission at 380 nm	UV/Visual Spectroscopy	%	35
THERMAL			
Shrinkage at 150°C (302 F)	ASTM D1204-02		
-Machine Direction		%	1.49
-Web Direction		%	1.30

Notes

- All tests are done with 0.015" thick sample.
- Taber abrasion used 100 cycles with CS10F wheels and 500 grams load. ™ Trademark of SABIC.

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe

Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

¹ Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs



LEXAN is a trademark of SABIC.