

LEXAN™ FR700NV FILM

PRODUCT DATASHEET

DESCRIPTION

Lexan™ FR700NV is a black, one side fine matte, one side velvet flame-retardant polycarbonate film with a UL94 V-0 listing at 0.430 mm. As a non-aesthetic version of FR700, this film provides good value for internal insulation components while maintaining temperature and flame performance. This film has excellent mechanical properties, good dimensional stability at high temperatures and a high flammability rating, making it good for applications such as power supply flat insulation, disc drive insulation, key board insulation, business equipment insulation and has insulation and EMI/RFI shielding when laminated with metal foil.

TYPICAL PROPERTY VALUES ◆

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
MECHANICAL						
Tensile Strength @ Yield (0.43mm)	ASTM D882	Psi	10300	ISO 527	MPa	67
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	62
Tensile Modulus (0.43mm)	ASTM D882	psi	35800	ISO 527	MPa	2485
Tensile Elongation at Break (0.43mm)	ASTM D882	%	68	ISO 527	%	68
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	8		J	10
Tear Strength – Initiation	ASTM D1004	lb/mil	1.24		kN/m	218
Tear Strength – Propagation	ASTM D1922	g/mil	40		kN/m	15.5
THERMAL						
Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.2
Specific Heat @40°F (4°C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417 / D3418	°F	307	ISO 11357	°C	153
Shrinkage at 302°F (150°C) Transverse Direction	ASTM D1204	%	0.03		%	0.03
Shrinkage at 302°F (150°C) Machine Direction	ASTM D1204	%	0.4		%	0.4
Heat Deflection Temp. TMA at 1.8 Mpa	ASTM D1204	°F	290	ISO 75 Modified	°C	145
PHYSICAL						
Density	ASTM D792	slug/ft ³	2.5	ISO 1183	kg/m ³	1300
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35

ELECTRICAL

Dielectric Strength in oil, short time @ 72°F (23°C), 10 mils (0.25mm) Dielectric Constant	ASTM D149-97a Method A	kV/mil	1.5	IEC 60243	kV/mm	59
@ 60 Hz	ASTM D150	-	2.9	IEC 60250	-	2.9
@1,000,000 Hz	ASTM D150	-	2.8	IEC 60250	-	2.8
Dissipation Factor						
@ 60 Hz	ASTM D150	-	0.0026	IEC 60250	-	0.0026
@1,000,000 Hz	ASTM D150	-	0.0117	IEC 60250	-	0.0117
Volume Resistivity	ASTM D257	Ω - cm	1.00E+17	IEC 60093	Ω - cm	1.00E+17
Surface Resistivity	ASTM D257	Ω /square	1.00E+16	IEC 60093	Ω /square	1.00E+16
Arc Resistance, Tungsten Electrodes	ASTM D495	s	64			

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC Innovative Plastics, Specialty Film & Sheet representative or the Quality Services Department. Reported values are based on 0.430 mm (0.017") thickness film unless otherwise noted.

™ Trademarks of SABIC.

UL file numbers: [E121562](#), [E207780](#), [E45329](#)

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.017 - 0.030" (0.43 - 0.750mm)	-/+ 5%

COLORS STANDARD: **Black Color – 701 (BK)**

CONTACT US:

Middle East and Africa
SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Americas
Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe
Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific
Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

Email
sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

