

# LEXAN™ H6000 SHEET

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ H6000 sheet is a high modulus, non-Chlorinated and non-Brominated compliant flame retardant opaque polycarbonate based sheet range available in standard and custom colors. In addition to good flammability performance, it offers excellent impact resistance, good stiffness and strength and ease of processing, making it an excellent candidate for a wide variety of applications in industries such as electrical/electronics and transportation (e.g. rail, bus).

### TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
<b>PHYSICAL</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.28
Water absorption, 50% RH, 23 °C	ISO 62	%	0.1
Water absorption, saturation, 23°C	ISO 62	%	0.3
<b>MECHANICAL</b>			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	4
Nominal strain at break 50 mm/min	ISO 527	%	50
Tensile modulus 1 mm/min	ISO 527	MPa	3300
Flexural strength 2 mm/min	ISO 178	MPa	100
Flexural modulus 2 mm/min	ISO 178	MPa	3350
<b>THERMAL</b>			
Vicat softening temperature, B/120	ISO 306	°C	114
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75	°C	89
<b>OPTICAL</b>			
Light transmission 3 mm	ASTM-D1003	%	n/a
<b>FIRE RATINGS</b>			
<b>Rail</b>			
France	NF P 92-501	-	M1 (2mm)
France	NF F 16-101	-	F2 (2mm)
Poland	PN-K-02512	-	R1 (2mm)
<b>Electrical</b>			
Vertical burn (50W)	UL94V	-	V0 (1.5mm)

◆ Typical values only. Variations within normal tolerances are possible for the various textures.  
 ™ Trademark of SABIC.

---

## PROCESSING

LEXAN™ H6000 sheet is ideally suited to thermoforming. Sandwich type heating systems give the best results. Lexan H6000 sheet has a forming temperature range of 160 - 200°C. When forming, a draft angle of at least 3° should be allowed, and post mold shrinkage of 0.4 – 0.6% taken into account.

## PRE-DRYING

It is important to ensure that Lexan H6000 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 100°C is recommended. Pre-drying is advised based on 2 hours/mm thickness

## ASSEMBLING

Parts made from Lexan H6000 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC Specialty Film & Sheet representative for advice on specific applications.

## PAINTING

LEXAN H6000 sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available upon request.

## CHEMICAL RESISTANCE

LEXAN H6000 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the LEXAN H6000 sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance.

## PRODUCT AVAILABILITY

**Product code:** LEXAN™ H6000  
**Textures:** Polished/Suede (H6006), Polished/Haircell (H60011N)

See product availability guide for available gauges, sizes, and colors

---

## CONTACT US:

### Middle East and Africa

SABIC Global Headquarters  
PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
F +966 (0) 1 225 9000  
E info@sabic.com

### Email

sfs.info@sabic-ip.com

### Americas

Specialty Film & Sheet  
1 Plastics Avenue  
Pittsfield, MA 01201  
USA  
Toll-free 1 800 323 3783  
T 1 413 448 6655  
F (888) 443 2033  
E Spinside.sales@sabic-ip.com

### Europe

Specialty Film & Sheet  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 (0)164 293678  
F +31 (0)164 293272  
E sfs.info@sabic-ip.com

### Asia Pacific

Specialty Film & Sheet  
2550 Xiupu Road  
Pudong  
201319 Shanghai  
China  
T +86 21 2037 8188  
F +86 21 2037 8288  
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.  
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

[www.sabic.com/sfs](http://www.sabic.com/sfs)

