

LEXAN™ 9440 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 9440 uncoated polycarbonate sheet is formulated to meet the requirements of specialty applications as food handling/contact, medical device/apparatus, and other clean room needs. LEXAN 9440 sheet complies with FDA food additive regulations (21 CFR 177.1580) and meets USP-VI criteria. LEXAN 9440 sheet offers high impact performance, thermoform ability, transparency and dimensional stability.

TYPICAL PROPERTY VALUES ♦

PROPERTY	TEST METHOD	UNITS	VALUE
Physical			
Specific Gravity	ASTM D792	-	1.20
Water absorption, equilibrium, 24 Hrs.	ASTM D570	%	0.15
@ 73° F			0.35
@ 212° F			0.58
Light Transmission (avg.) 1/8" disk	ASTM D1003	%	88
Mechanical			
Tensile Strength	ASTM D638	psi	
@ Yield			9,000
@Ultimate			9,500
Elongation	ASTMD638	%	110
Tensile Modulus	ASTM D638	psi	345,000
Flexural Modulus	ASTM D790	psi	345,000
Flexural Strength	ASTM D790	psi	13,500
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTMD695	psi	345,500
Elongation	ASTM D638	%	110
Izod Impact Strength,	ASTM D256A	ft-lbs/in	
Notched @ 1/8"			12-16
Unnotched @ 1/8"			60 (no failure)
Thermal			
Heat deflection temperature	ASTM D648	°F	
@ 264 psi			270
@ 66 psi			280
Coeff.of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 ⁻⁵
Thermal Conductivity	ASTM C177	Btu/hr x ft ² x °F x in	1.35

♦ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

™ Trademarks of SABIC.

UL File Number: E121562

PRODUCT AVAILABILITY

Product code: LEXAN 9440 – polycycling masking
LEXAN 9444 – cling stick white masking

Standard size: 48 x 96 inches

Textures: Polished/Polished

Colors: Clear 112

Other colors/sizes are available by special request.

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe

Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

[†] Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

