

LEXAN™ SGC44-OB SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ SGC44-OB polish/polish sheet is an optical bright light diffuser sign grade. This extruded polycarbonate sheet offers significant advantages over many other sign materials in terms of design freedom, aesthetics and weathering properties. It combines high impact resistance with light diffusion properties that provides excellent protection against vandalism. LEXAN SGC44-OB sheet is available in optical bright opal white color with diffusion properties for uniform illumination. The top surface of LEXAN SGC44-OB sheet is UV-resistant giving excellent durability to outdoor weathering. LEXAN SGC44-OB sheet is an excellent candidate for a variety of sign industry applications ranging from back lighted and pole mounted signs, through channel letters to projection screens and roller shutters for advertisements.

TYPICAL PROPERTY VALUES ◆

PROPERTY	TEST METHOD	UNITS	VALUE
Physical			
Specific Gravity	ASTM D792	-	1.20
Water absorption, 24 hours	ISO 62	mg /ounce	10/00035
Water absorption, saturation /23°C	ISO 62	%	0.35
Mechanical			
Tensile stress at yield 50 mm/min	ASTM D638	Mpa / Kpsi	60/8.7
Tensile stress at break 50 mm/min	ASTM D638	Mpa / Kpsi	70/10.2
Tensile strain at yield 50 mm/min	ASTM D638	%	6
Tensile strain at break 50 mm/min	ASTM D638	%	120
Tensile Modulus 1 mm/min	ASTM D638	Mpa / Kpsi	2300/333.6
Flexural stress at yield 2 mm/min	ASTM D790	Mpa / Kpsi	90/13.1
Flexural Modulus 2 mm/min	ASTM D790	Mpa / Kpsi	2300/333.6
Impact			
Charpy impact, notched	ISO 179/2C	kJ/m2 / Klb/ft	35/2.4
Izod impact, unnotched 23°C	ASTM D256A	kJ/m2 / Klb/ft	NB
Izod impact, unnotched -30°C	ASTM D256A	kJ/m2 / Klb/ft	NB
Izod impact, notched 23°C	ASTM D256A	kJ/m2 / Klb/ft	65/4.5
Izod impact, notched -30°C	ASTM D256A	kJ/m2 / Klb/ft	10/0.7
Thermal			
Vicat Softening Temperature, Rate B/120	ASTM D648	°C / F	145/293
HDT/ Ae, 1.8 MPa edgew. 120*1*04/sp=100	ISO 75/Be	°C / F	138/280
Thermal Conductivity	ISO 8302	W/m °C	0.2
Coeff. of Thermal Expansion extr. 23-80°C	ASTM D696	1/°C / 1/F	7.10-5/4.10-5
Optical			
Light transmission WH7C154X [at 0.177"]	ASTM-D1003	%	36
Light diffusion factor [at 0.177"]	DIN 5036	--	0.83
Flammability			
UL Flammability (.060" min.)	UL94		HB ¹

◆ These These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. If minimum certifiable properties are required please contact your local SABIC Innovative Plastics representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples.

Light transmission value and light diffusion may vary by + or -4 %.

1 Expected value based on this being a LEXAN product, testing is in process

™ LEXAN is a trademark of SABIC.

UL File Number: E121562

OPTICAL PROPERTIES

Gauge / color grade	Light Transmission (%)	Diffusion Factor
.118"/ WH7C154X	45 ± 4%	0.83
.150"/ WH7C154X	39 ± 4%	0.83
.177"/ WH7C154X	35 ± 4%	0.83

UV PROTECTION

LEXAN SGC44-OB sheet has proprietary UV protected surfaces, giving excellent durability to outdoor weathering. The superior UV protected surface treatment is not affected by forming and fabricating and LEXAN SGC44-OB sheet is therefore backed by a 10 years warranty ± against yellowing, loss of light transmission and breakage. ± see warranty for details.

LEXAN SG sheet is essentially opaque to all wave lengths below 385 nanometers. This useful shielding property prevent discoloration of second surface graphics applied to the reverse side.

PRODUCT AVAILABILITY

LEXAN™ SGC44-OB sheet is available in form of sheets as well as on economical spools, making it easy to cut into desired sizes.

SHEET

GAUGE (INCHES)

.118, .150, .177

Standard Sizes (inches):

Widths: 52, 76, 100 web¥
Length: 100

Spools

Gauge (inches):

.118, .150, .177

Standard Sizes (inches):

Widths: 52, 64, 76, 100 web¥

Other Gauges may be available upon request

Standard optical bright white color: **WH7C154X**

Masking:

Top side: co-ex white PE with no print, UL tape

Bottom side: co-ex white PE with no print, "footage tape" on coils

¥web width is full extrusion from die, including the bead line, which is typically 2" of each side of the sheet.

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic-ip.com

Americas

Specialty Film & Sheet
1 Plastics Avenue
Pittsfield, MA 01201
USA
Toll-free 1 800 323 3783
T 1 413 448 6655
F (888) 443 2033
E Spinside.sales@sabic-ip.com

Europe

Specialty Film & Sheet
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic-ip.com

Asia Pacific

Specialty Film & Sheet
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic-ip.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2014 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs

