

FUNCTIONAL FORMS

LEXAN™ MRAC SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN MRAC flame-retardant sheet is a two-side, hard-coated polycarbonate material offering excellent impact resistance, optical clarity and the state-of-the-art in abrasion and UV resistance. LEXAN MRAC sheet is specifically designed for aircraft window dust covers, acoustical panels, visors, diffusers, and any other similar application not requiring forming.

PROPERTIES	Unit	Typical Value (◆)	Test Method
PHYSICAL			
Specific Gravity (color dependent)	-	1.2-1.27	ASTM D729
Water Absorption, Equilibrium, 24 hrs.	%	.20	ASTM D570
Sound Transmission (STC Ratings 36"x84")			ASTM E9070
@ .125"		25	
@ .187"		29	
Abrasion Resistance, CS10F wheels, 500 gram load, 100 cycles	%	1-4	ASTM D1044-76
MECHANICAL			
Tensile Strength @ Yield		10,000	ASTM D638
Tensile Strength ultimate		9,500	ASTM D638
Tensile Modulus	psi	245,000	ASTM D638
Tensile Elongation, Ultimate	%	>80	ASTM D638
Flexural Strength (Gauge Dependent) [#]	psi	14,000	ASTM D790
Flexural Modulus (Gauge Dependent) [#]	psi	350,000	ASTM D790
Dynatup Impact Strength, 1/2" dia. dart (Gauge Dependent) [#] @ 73°F	ft-lbs	50	ASTM D3763
Izod Impact Strength (Gauge Dependent) [#]	ft-lbs/in		ASTM D256A
Notched		2.4	
Unnotched		NB	ASTM D256A
Gardner Impact Strength, round tip (Gauge Dependent) [#] @ 73°F	in-lbs	>320	ASTM D3029
THERMAL			
Coefficient of Thermal Expansion	in/in/°F	3.75 x 10 ⁻⁵	ASTM D696
Heat Deflection Temperature @ 264 psi	°F	270	ASTM D648
FLAMMABILITY			
FAA Flammability @ .060" to .500"	-	Pass	FAR 25.853F1AI/ BSS 7230

- ◆ These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC representative.
- Trademark of SABIC

Abrasion Resistance Comparison

LEXAN MRAC sheet exhibits significantly less hazing than uncoated polycarbonate sheet as shown in the abrasion resistance chart.

	Test Method	% Haze		
		Uncoated Polycarbonate	LEXAN MRAC Sheet	Glass
Taber Abrasion 100 Cycles CS 10F	ASTM D 1044 Z26.1	35.0	<3	0.5

‡ The Taber Abrader test measures the percent of change in haze that results from the grinding action of two abrasive impregnated wheels on the test samples. A constant load of 500 grams is maintained as the samples rotate on a turntable for a predetermined number of revolutions.

Chemical Resistance

LEXAN MRAC sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. Specific (application related) testing is always advised, especially in applications where the MRAC sheet will come into contact with aggressive chemicals.



CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic.com

Americas

SABIC
Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

Europe

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic.com

Asia Pacific

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic.com

SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates.
© 2017 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

[†] Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors, which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

www.sabic.com/sfs