

FUNCTIONAL FORMS

LEXAN™ DLCW SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ DLCW Light Diffusion is a translucent polycarbonate sheet with unique light diffusing properties designed for indoor LED and conventional lighting fixtures. It features a unique combination of high light diffusion and high light transmission through a combination of optimized surface texture and advanced diffuser technology. This extruded polycarbonate sheet offers significant advantages over many other materials in terms of bright and uniform illumination, excellent impact resistance, design freedom and aesthetics. The sheet has a matte finish on one side and on the other side a polish finish with protective film masking.

PROPERTIES	Unit	Typical Value (◆)	Test Method
PHYSICAL			
Specific Gravity	-	1.2	ASTM D729
Moisture Absorption	%	.25	ASTM D570
MECHANICAL			
Elongation	%	110	ASTM D638
Tensile Strength @ Yield	MPa	61	ASTM D638
Tensile Strength ultimate	MPa	65	ASTM D638
Tensile Modulus	MPa	2510	ASTM D638
Flexural Strength	MPa	93	ASTM D790
Flexural Modulus	MPa	2201	ASTM D790
Izod Impact Notched	j/cm	6.4	ASTM D256A
Unnotched	j/cm	32	ASTM D256A
Shear Strength @ Yield	MPa	40	ASTM D732
Shear Modulus	MPa	786	ASTMD732
THERMAL			
Coefficient of Thermal Expansion	cm/cm/C	6.75x10-5	ASTM D696
OPTICAL			
Light Transmission	%	60-85	Internal
FLAMMABILITY			
UL Flammability		HB	UL94

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC, Specialty Film & Sheet representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.

™ Trademarks of SABIC.



CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Email

sfs.info@sabic.com

Americas

SABIC
Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

Europe

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic.com

Asia Pacific

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic.com

SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates.
© 2018 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

NOTICE: The information and data contained herein are believed to be correct and given in good faith, but because of the many particular factors, which are outside our knowledge and control and affect the use of product, no warranty is given or is to be implied with respect to such information, nor do we offer any immunity against infringement.

www.sabic.com/sfs
