

LEXAN™ MARGARD™

HLGA2 Sheet

PRODUCT DATASHEET

DESCRIPTION

High abrasion resistant, non-weatherable, LEXAN™ MARGARD™ HLGA2 sheet is an improved single-sided hard coated polycarbonate sheet offering excellent abrasion resistance, excellent dimensional stability, impact resistance, optical clarity and passes DIN 52305 A-AZ‡ for a specific gauge range. It is an excellent candidate for glass-LEXAN sheet laminates where LEXAN MARGARD HLGA2 sheet is being bonded by means of PU interlayer or polymers to the glass package creating a “no spall” glass/LEXAN laminate with improved abrasion resistant properties. LEXAN MARGARD HLGA2 sheet is suitable to be screen-printed at the uncoated side using screen-print inks, being compatible with LEXAN polycarbonate sheet.

TYPICAL PROPERTY VALUES◆

Property	Test Method	Units	Value
Physical			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
Mechanical			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
Taber haze - 100 cycles, 500 gram, CS-10F	ASTM D1044	%	0.5 - 1
Taber haze - 500 cycles, 500 gram, CS-10F	ASTM D1044	%	1 - 4
Thermal			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
Electrical			
Volume resistivity	IEC 60093	Ohm.cm	>10 ¹⁵
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
Optical			
Light transmission 1 mm	ASTM D1003	%	92
Light transmission 1.5 mm	ASTM D1003	%	92
Light transmission 2 mm	ASTM D1003	%	92
Light transmission 3 mm	ASTM D1003	%	91
Light transmission 4 mm	ASTM D1003	%	90
Light transmission 5 mm	ASTM D1003	%	90
Light transmission 6 mm	ASTM D1003	%	89
Light transmission 12 mm	ASTM D1003	%	85
Optical distortion 2 – 6 mm	DIN 52305/-A-AZ		0.02

◆ Some of the property values have been derived from LEXAN resin data for the material used to produce this sheet product.

™ LEXAN is a trademark of SABIC.

OPTICAL PERFORMANCE

The optical qualities of LEXAN™ MARGARD™ HLGA2 sheet are the result of constant research in order to help provide high values. This is ensured by in house testing of LEXAN sheets in 2 - 8 mm thickness according DIN 52305/-A-AZ which specifies optical requirements for glazing in vehicles. During the optical control phase, LEXAN MARGARD HLGA2 sheets are examined against a special background, called image magnification, for proper identification of optical imperfections. Our internal manufacturing specifications are under constant supervision of our ISO 9001 approved Quality Management department.

PROCESSING

Glass/LEXAN security glazing panels can be produced using different systems for bonding purposes. The autoclaving process is the most common way of laminating glass and LEXAN sheets by means of a polyurethane based interlayer. The differences in thermal behavior between glass and polycarbonate require a sufficient thick interlayer in order to avoid a high stress level. The glass surface needs to be primed for better bond strength with the polyurethane film; contact between primer and LEXAN must be avoided. To avoid air-inclusions, it is recommended to place the construction in a vacuum bag with constantly measured negative pressure of 0.9 bar during the lamination process. A different way of bonding glass and LEXAN MARGARD HLGA2 sheet is to cast a polymer between the different substrates. During the polymerisation process, adhesion takes place between glass and LEXAN sheet.

RIPPLE ORIENTATION

Ripple direction may play an important role in the optical performance of the sheet. This direction is indicated on the sheet masking. The surface which is foreseen with the -2-strips indicating grade and ripple direction, is hard coated.

FLAT APPLICATIONS ONLY

Due to its mar-resistant coating, LEXAN MARGARD HLGA2 sheet cannot be used in curved applications. It is intended for flat applications only.

CHEMICAL RESISTANCE

LEXAN MARGARD HLGA2 sheet has high resistance at the coated side to most chemicals. In applications where it will come into contact with aggressive chemicals, specific (application related) testing of the material is strongly recommended.

PRODUCT AVAILABILITY

Product Code : HLGA2 sheet
Thicknesses : 1, 1.5 mm;
standard size: 1220 x 2920 mm
Thicknesses: 2, 2.5, 3, 4, 4.5, 6, 12mm;
standard size: 2000 x 2920 mm
Standard Color: Clear/112

CONTACT US:

Middle East and Africa

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Americas

Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

Europe

Functional Forms
[Plasticslaan 1](#)
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E sfs.info@sabic.com

Asia Pacific

Functional Forms
2550 [Xiupu Road](#)
[Pudong](#)
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E sfs.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.
© 2018 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs
