

# LEXAN™ HP05Wxx FILM

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ HP05Wxx graphic film is a virtually glare free film that uses SABIC's unique coatings technology allowing high light transmission for clear and sharp graphics. This high-performance coated film also offers very good chemical and abrasion resistance with excellent UV resistance. These performance capabilities, along with ease of processing, make HP05Wxx film a good choice for outdoor graphic applications such as warning labels, outdoor menu boards and gasoline pumps graphics.

### TYPICAL PROPERTY VALUES

| PROPERTY                                | ASTM (ISO) TEST METHOD  | UNITS USCS (SI)                           | HP05Wxx    |
|---|-------------------------|---|------------|
| <b>MECHANICAL</b>                       |                         |   |            |
| Tensile Strength @ Yield                | ASTM D882 (ISO 527)     | psi (MPa)                                 | 8800 (60)  |
| Ultimate                                | ASTM D882 (ISO 527)     | psi (MPa)                                 | 9000 (62)  |
| <b>THERMAL</b>                          |                         |   |            |
| Vicat Softening Temperature, B          | ASTM 1525               | °F (°C)                                   | 320 (160)  |
| Heat Deflection Temp. by TMA at 1.8 MPa | ISO 75 Modified         | °F (°C)                                   | 290 (145)  |
| Shrinkage at 302°F (150°C)              | ASTM D1204              | %   | 1.50%      |
| <b>PHYSICAL</b>                         |                         |   |            |
| Density                                 | ASTM D792 (ISO 1183)    | slug/ft <sup>3</sup> (kg/m <sup>3</sup> ) | 2.3 (1200) |
| Pencil Hardness (coated surface)        | ASTM D3363              | -   | HB-F       |
| Taber Abrasion (CS10F, 500g, 50cycles)  | ASTM D1044              | delta Haze                                | <3         |
| <b>OPTICAL</b>                          |                         |   |            |
| Light Transmission                      | ASTM D1003              | %   | 92.5       |
| Yellowness Index                        | ASTM D1925              | %   | 0.7        |
| Haze                                    | ASTM D1003              | %   | 70         |
| Gloss over Flat Black @ 60°             | ASTM D523-60 (ISO 2813) | -   | 17         |
| Gloss over Flat Black @ 85°             | ASTM D523-60 (ISO 2813) | -   | 6          |
| UV% Transmission at 350 nm              | UV/Visual Spectroscopy  | %   | 0.5        |
| UV% Transmission at 360 nm              | UV/Visual Spectroscopy  | %   | 1.5        |
| UV% Transmission at 370 nm              | UV/Visual Spectroscopy  | %   | 8          |
| UV% Transmission at 380 nm              | UV/Visual Spectroscopy  | %   | 38         |

◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department.

Reported Values are based on 0.030" (0.750 mm) Thickness unless otherwise noted.

™ Trademark of SABIC.

## MANUFACTURING SPECIFICATIONS

| NOMINAL GAUGE RANGES | MIN./MAX LIMIT OF NOMINAL |
|----------------------|---------------------------|
| 0.010" (0.250 mm)    | - 10%/+20%                |
| 0.015" (0.375 mm)    | - 5%/+12%                 |
| 0.020" (0.500 mm)    | -5%/+10%                  |
| 0.030" (0.750 mm)    | -8%/+8.5%                 |

## UV RESISTANCE

LEXAN™ HP05Wxx film utilizes a proprietary coating technology developed by SABIC. This special coating resists yellowing and hazing. Yellowness index change of less than 3.0 at 1000 hours of QUV testing and less than 2.0 at 1000 hours of Xenon Arc testing make LEXAN™ HP05Wxx film a candidate for demanding outdoor applications.

## TABER ABRASION RESISTANCE (ASTM D1044) LEXAN™ HP05Wxx GRAPHIC FILM

| CONDITION<br>CS10F WHEEL, 500 GRAMS | UNITS            | HP05Wxx |
|-------------------------------------|------------------|---------|
| 25                                  | Change in % Haze | 1.8     |
| 50                                  | Change in % Haze | 2.3     |
| 100                                 | Change in % Haze | 3.4     |
| 200                                 | Change in % Haze | 6.6     |

## CHEMICAL RESISTANCE

| CHEMICAL  | RESULTS† |
|---|----------|
| <b>One Hour Continuous Surface Contact at 73° F</b> |          |
| Acetone   | Failed   |
| MEK   | Failed   |
| Toluene   | Failed   |
| Methylene Chloride                                  | Failed   |
| Isopropyl Alcohol                                   | Passed   |
| Cyclohexanone                                       | Passed   |
| Ethyl Acetate                                       | Failed   |
| Xylene  | Passed   |
| 40% NaOH  | Passed   |
| Concentrated HCl                                    | Passed   |
| Gasoline (Regular)                                  | Passed   |
| Gasoline (Unleaded)                                 | Passed   |
| Butyl Cellosolve                                    | Passed   |

## CHEMICAL RESISTANCE

### 24 HOUR CONTINUOUS SURFACE CONTACT AT 120°F

|                                    |        |
|------------------------------------|--------|
| Coffee                             | Passed |
| Top Job <sup>†</sup>               | Passed |
| Fantastik <sup>##</sup>            | Passed |
| Formula 409 <sup>#</sup>           | Passed |
| Windex w/ Ammonia D <sup>###</sup> | Passed |
| Wisk <sup>¶</sup>                  | Passed |
| Downy <sup>#</sup>                 | Passed |
| Spray N Wash <sup>##</sup>         | Passed |
| Clorox <sup>*</sup>                | Passed |
| Mustard                            | Passed |
| Mr. Clean <sup>#</sup>             | Passed |
| Ketchup                            | Passed |
| Tea                                | Passed |
| Tomato Juice                       | Passed |
| Lemon Juice                        | Passed |
| Grape Juice                        | Passed |
| Vinegar                            | Passed |
| Milk                               | Passed |

- † Failure constitutes any of the following: non-removable stain or cloudiness, blistering, delamination, or cracking of the coating or failure to pass crosshatch tape adhesion.
- ¶ Wisk is a registered trademark of Lever Brothers Company
- # Formula 409 and Clorox are registered trademarks of the Clorox Company
- # Top Job, Downy, and Mr. Clean are registered trademarks of Procter & Gamble
- ## Fantastik and Spray 'N Wash are registered trademarks of Texize, Division of Norton Norwich Products, Inc.
- ### Windex w/Ammonia D is a registered trademark of Drackett Products Company



## CONTACT US:

### Middle East and Africa

SABIC Global Headquarters  
PO Box 5101  
Riyadh 11422  
Saudi Arabia  
T +966 (0) 1 225 8000  
F +966 (0) 1 225 9000  
E [info@sabic.com](mailto:info@sabic.com)

### Email

[sfs.info@sabic-ip.com](mailto:sfs.info@sabic-ip.com)

### Americas

Specialty Film & Sheet  
1 Plastics Avenue  
Pittsfield, MA 01201  
USA  
Toll-free 1 800 323 3783  
T 1 413 448 6655  
F (888) 443 2033  
E [Spinside.sales@sabic-ip.com](mailto:Spinside.sales@sabic-ip.com)

### Europe

Specialty Film & Sheet  
Plasticslaan 1  
4612 PX  
Bergen op Zoom  
The Netherlands  
T +31 (0)164 293678  
F +31 (0)164 293272  
E [sfs.info@sabic-ip.com](mailto:sfs.info@sabic-ip.com)

### Asia Pacific

Specialty Film & Sheet  
2550 Xiupu Road  
Pudong  
201319 Shanghai  
China  
T +86 21 2037 8188  
F +86 21 2037 8288  
E [sfs.info@sabic-ip.com](mailto:sfs.info@sabic-ip.com)

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates.  
© 2019 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

[www.sabic.com/sfs](http://www.sabic.com/sfs)