


LEXAN™ DLCW SHEET


PRODUCT DATASHEET

DESCRIPTION

LEXAN™ DLCW Light Diffusion is a translucent polycarbonate sheet with unique light diffusing properties designed for indoor LED and conventional lighting fixtures. It features a unique combination of high light diffusion and high light transmission through a combination of optimized surface texture and advanced diffuser technology. This extruded polycarbonate sheet offers significant advantages over many other materials in terms of bright and uniform illumination, excellent impact resistance, design freedom and aesthetics. The sheet has a matte finish on one side and on the other side a polish finish.

TYPICAL PROPERTY VALUES

PROPERTIES	Unit	Typical Value 	Test Method
PHYSICAL			
Specific Gravity	-	1.2	ASTM D729
Moisture Absorption	%	.25	ASTM D570
MECHANICAL			
Elongation	%	110	ASTM D638
Tensile Strength @ Yield	MPa	61	ASTM D638
Tensile Strength ultimate	MPa	65	ASTM D638
Tensile Modulus	MPa	2510	ASTM D638
Flexural Strength	MPa	93	ASTM D790
Flexural Modulus	MPa	2201	ASTM D790
Izod Impact Notched	J/cm	6.4	ASTM D256A
Unnotched	J/cm	32	ASTM D256A
Shear Strength @ Yield	MPa	40	ASTM D732
Shear Modulus	MPa	786	ASTMD732
THERMAL			
Coefficient of Thermal Expansion	cm/cm/C	6.75x10-5	ASTM D696
OPTICAL			
Light Transmission	%	60-85	Internal
FLAMMABILITY			
UL flammability		HB	UL94

 These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC, Specialty Film & Sheet representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection molded samples. All samples are prepared according ISO 294.
™ Trademarks of SABIC.

DLCW is f1 rated as suitable for outdoor use with respect to exposure to ultraviolet light, water exposure and immersion in accordance with UL 746C



CONTACT US:

SABIC CORPORATE HQ

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Americas

SABIC
Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

Europe

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E ff.info@sabic.com

Asia Pacific

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with TM are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2020 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.