

LEXAN™ LIGHT F6L300 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ LIGHT F6L300 sheet offers the lightest thermoplastic sheet option for thermoformed aircraft interiors parts, with a specific gravity of 0.85 g/cm³. It offers up to 40% weight savings when replacing traditional polyvinyl chloride and acrylic blend (PVC/PMMA) -based sheet products for potential applications such as seating parts, cockpit dashboard enclosures, partitions, luggage compartments and passenger service units. Available with a variety of textures and virtually any colour, LEXAN LIGHT sheet meets typical industry flame, smoke density and toxicity requirements.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Sheet thickness availability	SABIC Internal	mm	1.5 – 3.2
Specific gravity	SABIC Internal	g/cm ³	0.85
Water absorption, saturation, 23°C	SABIC Internal	%	0.51
MECHANICAL			
Tensile Strength at Yield, 50mm/min	ASTM D 638	MPa	30
Tensile Modulus at Yield, 50mm/min	ASTM D 638	MPa	1260
Elongation at Yield, 50mm/min	ASTM D 638	%	6
Elongation at Break, 50mm/min	ASTM D 638	%	24
Flexural Stress @ Yield, 1.27mm/min	ASTM D 790	MPa	61
Flexural modulus, 1.27mm/min	ASTM D 790	MPa	1630
IMPACT			
Izod impact, unnotched 23°C, 5lbf/ft	ASTM D256	J/m	807
Izod impact, notched 23°C, 5lbf/ft	ASTM D256	J/m	320
Ductility	ASTM D256	%	100
Instrumented Impact Total Energy, 23°C @ 3mm	ASTM D3763	J	30
Instrumented Impact Energy to Max Load, 23°C @ 3mm	ASTM D3763	J	19
THERMAL			
Vicat softening temperature, 50N, 120°C/h	ASTM D 1525	°C	144
Heat deflection temperature, 1.82MPa	ASTM D 648	°C	126
Coefficient of linear thermal expansion, -60-160°C	SABIC Internal	um/(m·°C)	69
OPTICAL			
Light transmission	ASTM-D1003	%	Opaque
FIRE RATINGS			
Aircraft			
Vertical burn, 60 s	FAR 25.853(a)+App.F	-	Pass
Smoke density	ABD0031	-	Pass < 150
Smoke toxicity	ABD0031,BSS 7239	-	Pass
Electrical			
Vertical burn (50W)	UL 94	-	V0

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. If minimum certifiable properties are required please contact your local SABIC, Specialty Film & Sheet representative. All values are

measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on extruded sheet samples.

* Typical values only. Variations within normal tolerances are possible. ™ Trademarks of SABIC.

PROCESSING

LEXAN LIGHT F6L300 sheet can be thermoformed into complex 3D shaped parts with very thin walls, offering substantial potential for overall weight savings and fuel efficiency across an airline fleet. It can be formed into complex shapes using standard thermoforming equipment. LEXAN LIGHT sheet has a forming temperature range of 170 - 225 °C. It is recommended that the forming tool be pre-heated at 110 – 120 °C. When forming, a draft angle of at least 3° should be allowed (7 ° for male molds), and post mold shrinkage of 0.9 – 1.1% taken into account, depending on mold temperature.

PRE-DRYING

It is important to ensure that LEXAN LIGHT F6L300 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120 °C is recommended, with a 25 mm gap between sheets. Pre-drying times vary from 3-12 hours for 1.5 to 3.2 mm thick sheets.

ASSEMBLING

Parts made from LEXAN LIGHT F6L300 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC Film & Sheet representative for advice on specific applications.



CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 292272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES (“SELLER”) ARE SOLD SUBJECT TO SELLER’S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER’S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER’S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller’s materials, products, services or recommendations for the user’s particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller’s Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.