

LEXAN™ 8B35V FILM

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 8B35V Film is a one-side velvet, one side matte transparent polycarbonate film for applications, which require UL94 flammability performance. It offers high temperature resistance, excellent dimensional stability, as well as good printability without pre-treatment making it an excellent candidate for multi-layer printing for applications such as overlays, floor graphics, high performance labels and in-mould decoration. It can be screen printed using traditional solvent based or water based inks, as well as UV or infrared drying inks and offers ease of processing for thermoforming, embossing, die cutting, hydro-forming and bending. The velvet texture offers mar resistance, and can be used over light-emitting devices (LEDs).

TYPICAL PROPERTY VALUES

PROPERTY	ASTM TEST METHOD	UNITS (USCS)	VALUE	ISO TEST METHOD	UNITS (SI)	VALUE
Tensile Strength @ Yield	ASTM D882	Psi	8349	ISO 527	MPa	60.9
Tensile Strength @ Yield	ASTM D882	psi	8500	ISO 527	MPa	62
Ultimate	ASTM D882	psi	9000	ISO 527	MPa	65
Tensile Modulus	ASTM D882	psi	300000	ISO 527	MPa	2506
Tensile Elongation at Break	ASTM D882	%	100-160	ISO 527	%	100-154
Gardner Impact Strength at 0.03" (0.75 mm)	ASTM D3029	ft-lb	23	ISO 6603-1	J	31
Tear Strength						
Initiation	ASTM D1004	lb/mil	1.4-1.8		kN/m	245
Propagation	ASTM D1922	g/mil	30-55		g/mil	10-20
Puncture Resistance (Dynatup)	ASTM D3763	ft-lb	9		J	12
Fold Endurance (MIT)						
0.010"(0.25 mm)	ASTM D2176-69	Double folds	60			
0.020"(0.50mm)	ASTM D2176-69	Double folds	20			

THERMAL

Coefficient of Thermal Conductivity	ASTM D5470	Btu/hr/ft ² /°F/in	1.35		W/m ² K	0.2
Coefficient of Thermal Expansion	ASTM E831	(x10 ⁻⁵ /°F)	3.2	ISO 11359	(x10 ⁻⁵ /°C)	5.8
Specific Heat @ 40 °F (4 °C)	ASTM E1269	Btu/lb/°F	0.3		KJ/Kg-°C	1.25
Glass Transition Temperature	ASTM D3417/D3418	°F	307	ISO 11357	°C	153
Vicat Softening Temperature, B	D3418	°F				
Heat Deflection Temp. by TMA at 1.8 MPa	ASTM 1525-00 Modified	°F	323	ISO 75 Modified	°C	160
Shrinkage at 302°F (150°C)	ASTM D1204	°F	1.40		%	1.40
Brittleness Temperature	ASTM D746	°F	-211		°C	-1.35

OPTICAL

Refractive Index @ 77 °F (25 °C)	ASTM D542A	-	1.6			
Light Transmission	ASTM D1003	%	80			
Yellowness Index	ASTM D1925	%	2.2			
Haze	ASTM D1003	%	102			
Gloss over Flat Black min/max @ 60°	ASTM D523-60	-				
UV cutout	UV/Visual	%				
	Spectroscopy	-	0.3			

PHYSICAL

Density	ASTM D792	Slug/ft ³	2.3	ISO 62	kg/m ³	1200
Water Absorption, 24 hrs.	ASTM D570	% change	0.35	ISO 62	% change	0.35
Surface Roughness (RMS)	ASTM D5946-01	L	See chart			
Surface Energy (1 st surface / 2 nd surface)	Dyne Pens	Dyne	37/31			
Surface Tension (1 st surface / 2 nd surface)	ASTM D3363	-	>44/38-40			
Taber Abrasion	ASTM D1044	Delta Haze	<1			

MANUFACTURING SPECIFICATIONS

NOMINAL GAUGE RANGES	MIN./MAX LIMIT OF NOMINAL
0.003" (0.075 mm)	± 10%
0.005-0.007" (0.125-0.175 mm)	± 8%
0.010-0.015" (0.250-0.375 mm)	± 5%
0.020-0.007" (0.500 mm)	± 3%

GLOSS BY GAUGE (ASTMD 523-60)

GAUGE ANGLE	ANGLE		VELVET	MATTE
VELVET				
0.003" (0.075 mm)	60°	Minimum	3	5
		Maximum	8	15
<0.005" – 0.020" (0.125 mm– 0.500mm)	60°	Minimum	3	5
		Maximum	4.5	15

RMS BY GAUGE

GAUGE		MATTE
0.003" (0.075 mm)	Minimum	45
	Maximum	165
<0.005" – 0.020" (0.125 mm–0.500mm)	Minimum	10
	Maximum	55

UL FLAMMABILITY RATING / PERFORMANCE LEVELS

THICKNESS	RATING
All GAUGES	UL94V-2
File Number	E207780/E121562

- ◆ These are typical properties and are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC representative or the SABIC Quality Services Department.
- ™ Trademark of SABIC

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 CityWest Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 293272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.
© Copyright 2020. All rights reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

