

LEXAN™ MARGARD™ FMR5XT (FORMABLE) SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ MARGARD™ FMR5 XT sheet is a transparent UV and abrasion resistant glazing material. Extremely high impact strength, with the capacity to be cold curved or drape formed. Two side formable coated, offers resistance against wear and tear.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.20
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
Taber haze - 100 cycles, 500 gram, CS-10F	ASTM D1044	%	4 - 8
THERMAL			
Vicat softening temperature, rate B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75-2	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 ⁻⁵
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
OPTICAL			
Light transmission 3 mm	ASTM D1003	%	90
Light transmission 4 mm	ASTM D1003	%	90
Light transmission 5 mm	ASTM D1003	%	89
Light transmission 6 mm	ASTM D1003	%	89
Light transmission 8 mm	ASTM D1003	%	88
Light transmission 9.5 mm	ASTM D1003	%	87
Light transmission 12 mm	ASTM D1003	%	85

◆ Some of the property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.
™ Trademark of SABIC.

CURVED APPLICATIONS

Design freedom, light weight and optical clarity combined with its superior mechanical properties makes LEXAN™ MARGARD™ FMR5 XT sheet an excellent candidate for shaped applications like: motor-bike windshields, curved windows (e.g. revolving doors), partitions, skylights, barrel vaults, balcony glazing, stair-glazing, shelters, machine - safety guards.

OPTICAL PERFORMANCE

Clear LEXAN MARGARD FMR5 XT sheet can offer excellent clarity and transmission in the visible light and near infrared region of the spectrum. As it is essentially opaque to all wavelengths below 385 nanometers, it is an excellent candidate for protecting art, antiques, retail displays and fabrics from damaging effects of UV rays. LEXAN MARGARD FMR5 XT sheet is based on high optical LEXAN sheet measured according to the DIN 52305 A AZ. LEXAN MARGARD FMR5 XT sheet is ANSI/SAE Z26.1 certified (3.00mm – 6.00mm).

CHEMICAL RESISTANCE

The mar-resistant coating of LEXAN MARGARD FMR5 XT sheet has sufficient resistance to common chemicals encountered in everyday use. Taking into account the complexity of chemical compatibility, we strongly recommend liaison with SABIC for testing of chemicals which come into contact with our LEXAN sheet products.

FIRE TEST PERFORMANCE

LEXAN MARGARD FMR5 XT sheet has good fire performance against many national fire codes dependent on thickness and color; please check with the local sales office for details.

UV PROTECTION

LEXAN MARGARD FMR5 XT sheet has proprietary UV protected surfaces, giving excellent durability to outdoor weathering and comes with a 5 year limited written warranty (see warranty for details).

IMPACT STRENGTH

LEXAN sheet offers outstanding impact strength and complies with the majority of international standards. With a thickness of 4 mm and upwards it complies with DIN 52290 part 4.

PROCESSING

LEXAN MARGARD FMR5 XT sheet can be cold curved into radii of > 300 times the thickness. It can also be drape-formed at a maximum temperature of 155°C, normally without pre-drying.

Masking must be removed from the sheet within 6 months after delivery.

RIPPLE ORIENTATION

Ripple direction may play an important role in the optical performance of the sheet. This direction is indicated on the sheet masking. The surface which is foreseen with the -2-strips indicating grade and ripple direction, is hard coated.

PRODUCT AVAILABILITY

Product code:	LEXAN MARGARD FMR5 XT
Standard gauge:	3-12mm
Standard sizes:	2000 x 3000 mm
Masking, Top side:	Co-ex opal white PE (matrix dot-printed grade-name)
Bottom side:	Co-ex opal white PE

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 292272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
1266 Nanjing Road (A)
16th Floor, Plaza 66
200040 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with TM are trademarks of SABIC or affiliates.
© Copyright 2021. All rights reserved.

† Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.



LEXAN is a trademark of SABIC