

# LEXAN™ CLINIWALL™ AC6200 SHEET

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ CLINIWALL™ sheet is a non-chlorinated and non-brominated opaque sheet with antibacterial properties against specifically E-coli and MRSA bacteria. AC6200 is available in standard and custom colours. In addition to good flammability and smoke performance, it offers excellent mechanical properties like impact, stain, blood and urine resistant combined with ease of processing, making it an excellent candidate for a wide range of applications in industries such interior wall cladding and sandwich panel.

### TYPICAL PROPERTY VALUES ◆

PROPERTY	TEST METHOD	UNITS	VALUE
<b>PHYSICAL</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.20
<b>MECHANICAL</b>			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Scratch resistance	Pensile Hardness	9H	No scratches
Flexural Strength (2mm/min)	ISO 178	MPa	90
Linear thermal expansion, 23-55°C	ISO 11359-2	mm	7x10 <sup>-5</sup> 1/°C
<b>IMPACT</b>			
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m <sup>2</sup>	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m <sup>2</sup>	70
<b>THERMAL</b>			
Vicat softening temperature, B/120	ISO 306	°C	145
<b>FIRE RATINGS</b>			
<b>Building &amp; Construction</b>			
Europe	EN13501-1	-	B,s1,d0
<b>ANTI-BACTERIAL PERFORMANCE</b>			
MRSA 35°C Reduction colony forming units after 24hrs	ISO 22196 / JIS Z 2801:2000	%	>99,9
E-COLI 35°C Reduction colony forming units after 24hrs	ISO 22196 / JIS Z 2801:2000	%	>99,999

- ◆ These property values have been derived from resin data for the material used to produce this sheet product. Variation within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required, please contact your local SABIC, Functional Forms representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All properties are measured on injection-molded samples. All samples are prepared according ISO 294.

™ Trademark of SABIC.

PROCESSING

LEXAN™ CLINIWALL™ sheet is suitable for cold line bending and can be mounted on a wall with a simple glue solution. For details we refer to our processing guide for AC6200 sheet.

LEXAN CLINIWALL sheet is suitable for thermoforming. To reach optimal results the materials needs to be heated with sandwich type heating systems to reach uniform heat uptake. Pre-drying of this material is necessary. Pre drying at 100°C for 2 hours /mm thickness

LEXAN CLINIWALL sheet has a processing window between 160 and 200°C. When forming, a draft angle of 3 degrees should be allowed. Post mould shrinkage is dependent on tool temperature and environmental circumstances, but will typically be in the range of 0.5-0.9%.

PRODUCT AVAILABILITY

PRODUCT CODE:	LEXAN CLINIWALL AC6200 sheet
TEXTURES:	Polished/Suede (AC6206), Polished/Silk Math (AC6205) on request with protective masking
COLORS:	WH6G057 (White), BR8G038 (Beige), GY8G179 (Light grey), GN6G033 (Mint green), BL8G009 (Light blue), BL1G038 (Dark blue), GY1G140 (Dark grey), GY7G160 (Medium grey), 86183 (Off white)
SIZES:	AC6205: Gauges 1.2 and 1.5mm, W – L = 1300 – 3050mm AC6206: Gauges 1.5 and 1.7mm, W – L = 1300 – 3050mm

CONTACT US:

<b>SABIC CORPORATE HQ</b> PO Box 5101 Riyadh 11422 Saudi Arabia T +966 (0) 1 225 8000 F +966 (0) 1 225 9000 E info@sabic.com	<b>AMERICAS</b> SABIC Functional Forms 2500 CityWest Boulevard Suite 100 Houston, TX 77042 USA Toll-free (800) 323 3783 F (888) 443 2033 E spinside.sales@sabic.com	<b>EUROPE</b> SABIC Functional Forms Plasticslaan 1 4612 PX Bergen op Zoom The Netherlands T +31 (0)164 293684 F +31 (0)164 293272 E ff.info@sabic.com	<b>PACIFIC</b> SABIC Functional Forms 2550 Xiupu Road Pudong 201319 Shanghai China T +86 21 3222 4500 F +86 21 6289 8998 E ff.info@sabic.com
--	--	---	---

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.  
© Copyright 2021. All rights reserved.

\* Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

