

# LEXAN™ F6000R SHEET

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ F6000R sheet is a flame retardant opaque recycle polycarbonate sheet product which is produced from internal regrind. In addition to good flammability performance, it offers excellent impact resistance, good stiffness and strength and ease of processing, making it suitable for a wide variety of applications in industries such as electrical/electronics and transportation (e.g. aircraft, rail).

### TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
<b>PHYSICAL</b>			
Density	ISO 1183	g/cm <sup>3</sup>	1.21
Water absorption, 50% RH, 23 °C	ISO 62	%	0.15
Water absorption, saturation, 23°C	ISO 62	%	0.35
<b>MECHANICAL</b>			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	6
Nominal strain at break 50 mm/min	ISO 527	%	>100
Tensile modulus 1 mm/min	ISO 527	MPa	2300
Flexural strength 2 mm/min	ISO 178	MPa	90
Flexural modulus 2 mm/min	ISO 178	MPa	2300
<b>IMPACT</b>			
Charpy impact, notched, 3.0 mm	ISO 179/1eA	kJ/m <sup>2</sup>	75
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m <sup>2</sup>	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m <sup>2</sup>	70
<b>THERMAL</b>			
Vicat softening temperature, B/120	ISO 306	°C	145
Temperature of deflection under load (type A), 1.8 MPa, flat	ISO 75	°C	127
Thermal conductivity	ISO 8302	W/m.°C	0.2
Coefficient of linear thermal expansion, 23-55°C	ISO 11359-2	1/°C	7x10 <sup>-5</sup>
Ball pressure test 125 ±2°C	IEC 60695-10-2	-	Pass
<b>ELECTRICAL</b>			
Volume resistivity	IEC 60093	Ohm.cm	>10 <sup>15</sup>
Dielectric strength, in oil, 3.2 mm	IEC 60243-1	kV/mm	18
<b>FIRE RATINGS</b>			
<b>Aircraft</b>			
Vertical burn, 60 s	FAR 25.583(a)+App.F	-	Pass (1-6mm)
Smoke density	ABD0031	-	Pass, Ds(4min)<150 (1-6mm)
Smoke toxicity	ABD0031,BSS 7239	-	Pass (1-6mm)
<b>Electrical</b>			
Limited Oxygen Index	ISO 4589-2	%	35

◆ Typical values only. Variations within normal tolerances are possible for the various textures.

™ Trademark of SABIC.

## PROCESSING

LEXAN™ F6000R sheet is ideally suited to thermoforming. It offers high, deep draw ratios, equal wall thickness distribution, and it can be formed into complex shapes using standard thermoforming equipment. Sandwich type heating systems give the best results. LEXAN F6000R sheet has a forming temperature range of 185 - 205°C. When forming, a draft angle of at least 3° should be allowed, and post mold shrinkage of 0.3 – 0.8% taken into account, depending on mold temperature.

## PRE-DRYING

It is important to ensure that LEXAN F6000R sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120°C is recommended. Pre-drying times vary from 3-12 hours for 1.2 to 4.0mm thick sheets.

## ASSEMBLING

Parts made from LEXAN F6000R sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC, Film & Sheet representative for advice on specific applications.

## PAINTING

LEXAN F6000R sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available upon request.

## CHEMICAL RESISTANCE

LEXAN F6000R sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the LEXAN F6000R sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance.

## PRODUCT AVAILABILITY

**Product code:** LEXAN F6000R  
**Textures:** Polished/Suede (F6006R)  
 See product availability guide for available gauges, sizes, and colors.

## CONTACT US:

### SABIC CORPORATE HQ

PO Box 5101  
 Riyadh 11422  
 Saudi Arabia  
 T +966 (0) 1 225 8000  
 F +966 (0) 1 225 9000  
 E info@sabic.com

### AMERICAS

SABIC  
 Functional Forms  
 2500 CityWest Boulevard  
 Suite 100  
 Houston, TX 77042  
 USA  
 Toll-free (800) 323 3783  
 F (888) 443 2033  
 E spinside.sales@sabic.com

### EUROPE

SABIC  
 Functional Forms  
 Plasticslaan 1  
 4612 PX  
 Bergen op Zoom  
 The Netherlands  
 T +31 (0)164 293684  
 F +31 (0)164 293272  
 E ff.info@sabic.com

### PACIFIC

SABIC  
 Functional Forms  
 2550 Xiupu Road  
 Pudong  
 201319 Shanghai  
 China  
 T +86 21 3222 4500  
 F +86 21 6289 8998  
 E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.  
 © Copyright 2021. All rights reserved.

<sup>1</sup> Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

