

LEXAN™ H6200 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ H6200 sheet is a non-Chlorinated and non-Brominated compliant flame retardant opaque pc/ABS based sheet available in standard and custom colors. In addition to good flammability performance, it offers excellent mechanical properties combining low temperature impact with strength and ease of processing, making it an excellent candidate for a wide range of applications in industries such as mass transportation.

TYPICAL PROPERTY VALUES

PROPERTY	TEST METHOD	UNITS	VALUE
PHYSICAL			
Density	ISO 1183	g/cm ³	1.19
MECHANICAL			
Yield stress 50 mm/min	ISO 527	MPa	>60
Yield strain 50 mm/min	ISO 527	%	5
Nominal strain at break 50 mm/min	ISO 527	%	8
Tensile modulus 1 mm/min	ISO 527	MPa	2500
IMPACT			
Izod impact, unnotched 23°C, 3.0 mm	ISO 180/1U	kJ/m ²	NB
Izod impact, notched 23°C, 3.0 mm	ISO 180/1A	kJ/m ²	45
THERMAL			
Vicat softening temperature, B/120	ISO 306	°C	118
OPTICAL			
Light transmission 3 mm	ASTM-D1003	%	n/a
FIRE RATINGS			
Building & Construction			
Europe	EN13501-1	-	b,s1,d0 (1.7mm)
Rail			
Germany	DIN 5510-2	-	S4/SR2/ST2(4mm) S3/SR2/ST2 (3mm)
Electrical			
Vertical burn (50W)	UL94V	-	V0 (1.5mm)

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product. Variations within normal tolerances are possible for various colors. These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC, Specialty Film & Sheet representative. All values are measured at least after 48 hours storage at 23°C/50% relative humidity. All samples are prepared according ISO 294.
™ Trademarks of SABIC.

PROCESSING

LEXAN™ H6200 is suitable for thermoforming. To reach optimal results the materials needs to be heated with sandwich type heating systems to reach uniform heat uptake. Pre-drying of this material is necessary. Pre drying at 100 °C for 2 hours /mm thickness.

LEXAN H6200 has a processing window between 160 and 200°C. When forming, a draft angle of 3 degrees should be allowed. Post mold shrinkage is dependent on tool temperature and environmental circumstances, but will typically be in the range of 0.5-0.9%.

CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

SABIC
Functional Forms
2500 CityWest Boulevard
Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

SABIC
Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293684
F +31 (0)164 293272
E ff.info@sabic.com

PACIFIC

SABIC
Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right.

SABIC and brands marked with ™ are trademarks of SABIC or affiliates.
© Copyright 2021. All rights reserved.

¹ Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

