

LEXAN™ 9600 SHEET

PRODUCT DATASHEET

DESCRIPTION

LEXAN™ 9600 sheet offers all the benefits of standard, transparent polycarbonate sheet - excellent impact resistance, good stiffness and strength, high optical quality, excellent formability, relatively light weight - but it has significantly better flammability characteristics, making it suitable for a wide variety of applications in the transportation, electrical and electronic industries.

TYPICAL PROPERTY VALUES◆

PROPERTY	TEST METHOD	UNITS	VALUE
Physical			
Density	ISO 1183	g/cm ³	1.24
Water absorption, equilibrium, 23°C	ISO 62	%	0.35
Rockwell Hardness	ASTM D785		M74
Mechanical			
Tensile Strength @ Yield	ISO 527	MPa	60
Tensile Strength, break	ISO 527	MPa	70
Tensile modulus	ISO 527	MPa	2350
Tensile elongation, break	ISO 527	%	120
Flexural strength, yield	ISO 178	Mpa	90
Flexural modulus	ISO 178	Mpa	2300
Izod notched impact, 23°C	ISO 180/1A	kJ/m ²	65
Gardner impact, 23°C	ASTM D3029	J	>40
-30°C		J	>40
Taber Abrasion, CS17, 1000g, 1000cycles	ASTM D1242	mg	9
Thermal			
Vicat Softening Temp, Rate B /120	ISO 306	°C	145
DTUL, 0.45 MPa	ISO 75/Be	°C	138
Thermal Conductivity	ASTM C 177	W/m°C	0.20
Mold Shrinkage	ISO 527	%	0.6-0.8
Coefficient of Thermal Expansion	ASTM D696	1/°C	7x10 ⁻⁵
Electrical			
Dielectric Strength	IEC 60243	kV/mm	17
Dielectric Constant, 60Hz			3.17
1 MHz			2.96
Dissipation Factor 50Hz	ASTM D150		0.001
1MHz			0.01
Volume Resistivity, 23°C	IEC 60093	Ohm.cm	>10 ¹⁵
Flammability Ratings			
UL 94	V-2 at 0.34" - 0.089" in Clear Only V-0 at 0.090" - 0.117" in Clear and Black only V-0 at 0.118" and above in all colors		
FAR 25.853	@ .030 - .125" Passes App F: 60-second and 12-second vertical, and 2.5 in./min. horizontal		

◆ These property values have been derived from LEXAN™ resin data for the material used to produce this sheet product.

™ Trademarks of SABIC.

PROCESSING

LEXAN™ 9600 sheet is ideally suited to thermoforming. It offers high, deep draw ratios, equal wall thickness distribution, and it can be formed into complex shapes using standard thermoforming equipment. Sandwich type heating systems give the best results. LEXAN 9600 sheet has a forming temperature range of 185 - 205°C. When forming, a draft angle of at least 3° should be allowed, and post mold shrinkage of 0.6 – 0.8% taken into account.

PRE-DRYING

It is important to ensure that LEXAN 9600 sheets are free of moisture prior to thermoforming. A hot air circulating oven set at 120°C is recommended. Pre-drying times vary from 3-24 hours, depending on sheet thickness.

ASSEMBLING

Parts made from LEXAN 9600 sheet can be assembled with plastics, metals, rubber and other materials using many types of adhesive bonding, welding and mechanical fastening techniques. Since some of these materials can cause environmental stress cracking, please consult SABIC Innovative Plastics for advice on specific applications.

PAINTING

LEXAN 9600 sheet is ideally suited for use with a wide variety of modern decoration techniques. A list of approved paint systems and suppliers is available on request.

CHEMICAL RESISTANCE

LEXAN 9600 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. In applications where the LEXAN 9600 sheet will come into contact with aggressive chemicals, specific (application related) testing is always advised. Effective painting systems can improve chemical resistance

FIRE TEST PERFORMANCE

LEXAN 9600 sheet has good fire performance against many national firecodes dependent on thickness and color; please check with the local sales office for details.

UL File Number: E121562

CONTACT US:

MIDDLE EAST AND AFRICA

SABIC Global Headquarters
PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

AMERICAS

Functional Forms
2500 City West Boulevard
Suite 100
Houston, TX 77042
USA
Inside sales:
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

EUROPE

Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 164 293684
F +31 164 292272
E ff.info@sabic.com

ASIA PACIFIC

Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 3222 4500
F +86 21 6289 8998
E ff.info@sabic.com



DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2021 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/sfs