

LEXAN™ FMR + FMR604 SHEET


PRODUCT DATASHEET

DESCRIPTION

The LEXAN™ FMR family of sheet products are two side hard coated polycarbonate materials offering excellent impact resistance, optical clarity and abrasion resistance. LEXAN FMR sheet may be cold-formed or heat-drape formed to soft radii. LEXAN FMR sheet is an excellent candidate for functional parts requiring exceptional toughness and surface hardness. Typical applications include motorcycle windscreens, race car windshields, industrial conveyor covers and aircraft components if LEXAN FMR604 is selected. Available in thicknesses from 0.125" through 0.500", LEXAN FMR sheet is easily fabricated on common equipment.

Applicable to the following grades: LEXAN™ FMRxxxx sheet, LEXAN™ FMRT102 sheet, LEXAN™ FMRTHD sheet and LEXAN™ FMR604 sheet (Aircraft grade).

TYPICAL PROPERTY VALUES

PROPERTIES	TEST METHOD	VALUE FMR	VALUE FMR604 	UNIT
PHYSICAL				
Specific Gravity	ASTM D792	1.2	1.2-1.26	-
Light Transmission (average at 0.118")	ASTM D1003	83		%
Initial Haze	ASTM D1003	<1	<1	%
Taber @ 100 cycles	ASTM D1004 (ANSI Z26.1)	10	<10	% haze
Chemical resistance	ANSI Z26.1	Pass	Pass	Pass/ Fail
Water absorption (24 hrs)	ASTM D570	0.15	0.15	%
Water absorption (Equilibrium)	@73 °F	0.35	0.35	%
Sound Transmission				
@ 0.125"	STC Rating	25	25	None
@ 0.187"	STC Rating	29	-	None
@ 0.250"	STC Rating	31	-	None
@ 0.375"	STC Rating	34	-	None
@ 0.500	STC Rating	34	-	None
MECHANICAL				
Tensile Strength @ Yield	ASTM D638		9,500	psi
Tensile Modulus	ASTM D638	345,000	240,000	psi
Flexural Strength	ASTM D790	13,500	14,000	psi
Flexural Modulus	ASTM D790	340,000	345,000	psi
Compressive Strength	ASTM D695	12,500	-	psi
Instrumented impact 1/2" dia. Dart (gauge dependent) @73F (average at 0.118")	ASTM D3763	40	40	ft-lbs

PROPERTIES	TEST METHOD	VALUE FMR	VALUE FMR604 (◆)	UNIT
THERMAL				
Coefficient of Thermal Expansion	ASTM D696	3.75 x 10 ⁻⁵	3.75 x 10 ⁻⁵	in/in/°F
Heat Deflection Temperature @ 264 psi	ASTM D648	270	280	°F
Heat Deflection Temperature @ 66 psi	ASTM D648	280		°F
FLAMMABILITY				
Horizontal Burn (Flame Spread) AEB	ASTM D635	<1	<1	in
Ignition Temperature, Self				-
Smoke density	FAR 25.853 (d) Apdx F, part V	-	Pass at 0.040 to 0.125"	Pass/ Fail
Vertical Burn (60 sec)	FAR 25.853 (a) Apdx F, Part I, (a), 1(i)	-	Pass at 0.040 to 0.125"	Pass/ Fail
Vertical Burn (12 sec)	FAR 25.853 (a) Apdx F, Part I, (a), 1(ii)	-	Pass at 0.040 to 0.125"	Pass/ Fail

◆ These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC representative.

™ Trademark of SABIC



CONTACT US:

SABIC CORPORATE HQ

PO Box 5101
Riyadh 11422
Saudi Arabia
T +966 (0) 1 225 8000
F +966 (0) 1 225 9000
E info@sabic.com

Americas

Functional Forms
2500 City West
Boulevard Suite 100
Houston, TX 77042
USA
Toll-free (800) 323 3783
F (888) 443 2033
E spinside.sales@sabic.com

Europe

Functional Forms
Plasticslaan 1
4612 PX
Bergen op Zoom
The Netherlands
T +31 (0)164 293678
F +31 (0)164 293272
E ff.info@sabic.com

Asia Pacific

Functional Forms
2550 Xiupu Road
Pudong
201319 Shanghai
China
T +86 21 2037 8188
F +86 21 2037 8288
E ff.info@sabic.com

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (i) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (ii) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2021 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.

www.sabic.com/ff