

# LEXAN™ MARGARD™ MRAC1 SHEET

## PRODUCT DATASHEET

### DESCRIPTION

LEXAN™ MARGARD™ MRAC1 flame-retardant sheet is a one-side, hard-coated polycarbonate material offering excellent impact resistance, optical clarity and the state-of-the-art in abrasion and UV resistance. LEXAN MARGARD MRAC1 sheet is specifically designed for aircraft window dust covers, acoustical panels, visors, diffusers, and any other similar application not requiring forming.

PROPERTIES	Unit	Typical Value (◆)	Test Method
<b>PHYSICAL</b>			
Specific Gravity (color dependent)	-	1.2-1.27	ASTM D729
Water Absorption, Equilibrium, 24 hrs.	%	.20	ASTM D570
Sound Transmission (STC Ratings 36"x84")			ASTM E9070
@ .125"		25	
@ .187"		29	
Abrasion Resistance, CS10F wheels, 500 gram load, 100 cycles	%	1-4	ASTM D1044-76
<b>MECHANICAL</b>			
Tensile Strength @ Yield		10,000	ASTM D638
Tensile Strength ultimate		9,500	ASTM D638
Tensile Modulus	psi	245,000	ASTM D638
Tensile Elongation, Ultimate	%	>80	ASTM D638
Flexural Strength (Gauge Dependent)#	psi	14,000	ASTM D790
Flexural Modulus (Gauge Dependent)#	psi	350,000	ASTM D790
Dynatup Impact Strength, 1/2" dia. dart (Gauge Dependent)# @ 73°F	ft-lbs	50	ASTM D3763
Izod Impact Strength (Gauge Dependent)#	ft-lbs/in		ASTM D256A
Notched		2.4	
Unnotched		NB	ASTM D256A
Gardner Impact Strength, round tip (Gauge Dependent)# @ 73°F	in-lbs	>320	ASTM D3029
<b>THERMAL</b>			
Coefficient of Thermal Expansion	in/in/°F	$3.75 \times 10^{-5}$	ASTM D696
Heat Deflection Temperature @ 264 psi	°F	270	ASTM D648

PROPERTIES	Unit	Typical Value (◆)	Test Method
FAA Flammability @ .060" to .500"	-	Pass	FAR 25.853F1A1/ BSS 7230

- ◆ These typical values are not intended for specification purposes. If minimum certifiable properties are required please contact your local SABIC representative.
- Trademark of SABIC

**Abrasion Resistance Comparison**

LEXAN™ MARGARD™ MRAC1 sheet exhibits significantly less hazing than uncoated polycarbonate sheet as shown in the abrasion resistance chart.

	Test Method	% Haze		
		Uncoated Polycarbonate	LEXAN MRAC1 Sheet	Glass
Taber Abrasion 100 Cycles CS 10F	ASTM D 1044 Z26.1	35.0	<3	0.5

‡ The Taber Abrader test measures the percent of change in haze that results from the grinding action of two abrasive impregnated wheels on the test samples. A constant load of 500 grams is maintained as the samples rotate on a turntable for a predetermined number of revolutions.

**Chemical Resistance**

LEXAN MARGARD MRAC1 sheet has sufficient resistance to most mineral oils, greases, aliphatic hydrocarbons and acids under low or moderate stress levels. Specific (application related) testing is always advised, especially in applications where the LEXAN MARGARD MRAC1 sheet will come into contact with aggressive chemicals.



**CONTACT US:**

**SABIC CORPORATE HQ**  
 PO Box 5101  
 Riyadh 11422  
 Saudi Arabia  
 T +966 (0) 1 225 8000  
 F +966 (0) 1 225 9000  
 E info@sabic.com

**AMERICAS**  
 SABIC  
 Functional Forms  
 2500 City West Boulevard  
 Suite 100  
 Houston, TX 77042  
 USA  
 Toll-free (800) 323 3783  
 F (888) 443 2033  
 E spinside.sales@sabic.com

**EUROPE**  
 SABIC  
 Functional Forms  
 Plasticslaan 1  
 4612 PX  
 Bergen op Zoom  
 The Netherlands  
 T +31 (0)164 293684  
 F +31 (0)164 292272  
 E ff.info@sabic.com

**PACIFIC**  
 SABIC  
 Functional Forms  
 2550 Xiupu Road  
 Pudong  
 201319 Shanghai  
 China  
 T +86 21 3222 4500  
 F +86 21 6289 8998

DISCLAIMER: THE MATERIALS, PRODUCTS AND SERVICES OF SAUDI BASIC INDUSTRIES CORPORATION (SABIC) OR ITS SUBSIDIARIES OR AFFILIATES ("SELLER") ARE SOLD SUBJECT TO SELLER'S STANDARD CONDITIONS OF SALE, WHICH ARE AVAILABLE UPON REQUEST. INFORMATION AND RECOMMENDATIONS CONTAINED IN THIS DOCUMENT ARE GIVEN IN GOOD FAITH. HOWEVER, SELLER MAKES NO EXPRESS OR IMPLIED REPRESENTATION, WARRANTY OR GUARANTEE (I) THAT ANY RESULTS DESCRIBED IN THIS DOCUMENT WILL BE OBTAINED UNDER END-USE CONDITIONS, OR (II) AS TO THE EFFECTIVENESS OR SAFETY OF ANY DESIGN OR APPLICATION INCORPORATING SELLER'S MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS. UNLESS OTHERWISE PROVIDED IN SELLER'S STANDARD CONDITIONS OF SALE, SELLER SHALL NOT BE RESPONSIBLE FOR ANY LOSS RESULTING FROM ANY USE OF ITS MATERIALS, PRODUCTS, SERVICES OR RECOMMENDATIONS DESCRIBED IN THIS DOCUMENT. Each user is responsible for making its own determination as to the suitability of Seller's materials, products, services or recommendations for the user's particular use through appropriate end-use and other testing and analysis. Nothing in any document or oral statement shall be deemed to alter or waive any provision of Seller's Standard Conditions of Sale or this Disclaimer, unless it is specifically agreed to in a writing signed by Seller. Statements by Seller concerning a possible use of any material, product, service or design do not, are not intended to, and should not be construed to grant any license under any patent or other intellectual property right of Seller or as a recommendation for the use of any material, product, service or design in a manner that infringes any patent or other intellectual property right. SABIC and brands marked with ™ are trademarks of SABIC or its subsidiaries or affiliates, unless otherwise noted.

© 2021 Saudi Basic Industries Corporation (SABIC). All Rights Reserved.

Any brands, products or services of other companies referenced in this document are the trademarks, service marks and/or trade names of their respective holders.